## RECEIVED **CENTRAL FAX CENTER**

Docket No. <u>JM 7343-2</u> Application No. 10/736,119

## AUG 0 3 2007

## AMENDMENTS TO THE CLAIMS:

303-978-2323

This listing of claims will replace all prior versions, and listings, of claims in the application:

## LISTING OF CLAIMS:

- 1. (Previously Presented) A woven, patterned glass fiber textile fabric comprised of a glass fiber yarn with a titer of from 270 to 300 tex as the warp, and a glass fiber yarn having a titer ranging from 68 to 660 tex as the weft.
- 2. (Original) The glass textile fabric of claim 1, wherein the titer of the warp yarn is in the range of from about 270 to 290 tex.
- 3. (Original) The glass textile fabric of claim 1, wherein the titer of the warp yarn is about 278 tex.
- 4. (Original) The glass textile fabric of claim 1, wherein the titer of the west yarn is in the range of from 190 to 350 tex.
- 5. (Original) The glass textile fabric of claim 1, wherein the titer of the west yarn is about 200 tex.
- 6. (Original) The glass textile fabric of claim 1, wherein the titer of the west yarn is about 330 tex.

Docket No. <u>JM 7343-2</u> Application No. <u>10/736,119</u> Page 3

- 7. (Original) The glass textile fabric of claim 1, wherein the warp density of the textile fabric ranges from 2.5 to 20 threads/cm.
- 8. (Previously Presented) The glass textile fabric of claim 7, wherein the warp density of the textile fabric is in the range of from about 6 to 10 threads/cm.
- 9. (Previously Presented) The glass textile fabric of claim 1, wherein the weft yarn density of the textile fabric is in the range of from about 2.0 to 12 threads/cm.
- 10. (Original) The glass textile fabric of claim 1, wherein the textile is impregnated with a chemical formulation comprised of a starch binder and a polymeric binder.

11-17. (Canceled)